

Collagen from Achilles Tendon (Smaller than 37 Micron)

Cat. No. CEFX-004

Lot. No. (See product label)

Introduction

Description All non-collagenous tissues of fresh bovine achilles tendon were removed and cut into small pieces. Extract at 0°C for 6 days and replace the Na₂HPO₄ solution several times to remove soluble proteins. Then extracted with 25% KCl solution at 0°C for 6 days to remove mucopolysaccharides. Finally, the residue was washed thoroughly with water, dehydrated with anhydrous ethanol, and air-dried. Insoluble; Nondenaturing Particle Size: Pass 40 Mesh (Smaller than 37 Micron)

Product Information

Species	Bovine
Source	Achilles Tendon
Form	Powder